## MLLG-POLE-WD-50-C1-T-SYP

50 Foot Wood Pole

Project Name	
i i ojece i tallic	_



## **DETAILS**

Southern Yellow Pine is species found south of the Mason-Dixon line and east of the Great Plains in the USA. It is known for its strength, stiffness, and density making it an ideal material for utility poles. It is effective in holding nails and other types of fasteners. The cellular structure makes it suitable for the pressure treatment process. Nearly 85% of all pressure-treated wood in the U.S. is southern yellow pine.



CCA Treated to Prevent Insect and Rot Damage



Up to 50+ Years Service



1-year warranty

OVERVIEW	
SKU: MLLG-POLE-WD-50-C1-T-SYP	
Warranty	1-year warranty
Species	
Treatment	CCA
ANSI Class	Class 1



## O PRODUCT FAMILY MODELS

SKU	Total Height	ANSI Class
MLLG-POLE-WD-50-C1-T-SYP	50 Feet	Class 1
MLLG-POLE-WD-50-C2-T-SYP	50 Feet	Class 2
MLLG-POLE-WD-50-C3-T-SYP	50 Feet	Class 3



## MLLG-POLE-WD-50-C1-T-SYP

50 Foot Wood Pole

Project Name	



WebID: 2250

PRODUCT SPECIFICATIONS				
	Total Height	50 Feet		
DIMENSIONS	Height Above Ground	43 Feet		
	Outside Diameter			
ANSI REQUIREMENTS	Weight Range	2350-2770 lbs		
	Treatment	CCA		
	Max Total Cross Arms	2-4		
	Max Total Cross Arms Per Side	1-2		
	Max Attached Weight Per Cross Arm	240 lbs		
	Min Circumference At Pole Top	27 Inches		
	Min Circumference 6 Feet From Butt	45 Inches		
	Min Diameter At Pole Top	8.594 Inches		
	Min Diameter 6 Feet From Butt	14.324 Inches		

