## MLLG-POLE-WD-55-C3-T-SYP

55 Foot Wood Pole

Project Name	
i i oject ivallie	



## **DETAILS**

Southern Yellow Pine is species found south of the Mason-Dixon line and east of the Great Plains in the USA. It is known for its strength, stiffness, and density making it an ideal material for utility poles. It is effective in holding nails and other types of fasteners. The cellular structure makes it suitable for the pressure treatment process. Nearly 85% of all pressure-treated wood in the U.S. is southern yellow pine.



CCA Treated to Prevent Insect and Rot Damage



Up to 50+ Years Service



1-year warranty

OVERVIEW				
SKU: MLLG-POLE-WD-55-C3-T-SYP				
Warranty	1-year warranty			
Species	Southern Yellow Pine			
Treatment	CCA			
ANSI Class	Class 3			



## **PRODUCT FAMILY MODELS**

SKU	Total Height	ANSI Class
MLLG-POLE-WD-55-C3-T-SYP		Class 3
MLLG-POLE-WD-55-C4-T-SYP		Class 4
MLLG-POLE-WD-60-C1-T-SYP		Class 1
MLLG-POLE-WD-60-C2-T-SYP		Class 2
MLLG-POLE-WD-60-C3-T-SYP		Class 3
MLLG-POLE-WD-60-C4-T-SYP		Class 4



## MLLG-POLE-WD-55-C3-T-SYP

55 Foot Wood Pole

Project Name		



WebID: 2256

PRODUCT SPECIFICATIONS				
DIMENSIONS	Total Height			
	Height Above Ground			
	Outside Diameter			
	Weight Range			
	Pole Height	55 ft		
	Height Above Ground	47.5 ft		
	Buried Depth Below Ground	7.5 ft		
	Weight Range	2070-2440 lbs		
	ANSI Class	3		
	Species	Southern Yellow Pine		
	Treatment	CCA		
ANSI REQUIREMENTS	Max Total Cross Arms	2-4		
	Max Total Cross Arms Per Side	1-2		
	Max Attached Weight Per Cross Arm	240 lbs		
	Min Circumference At Pole Top	23 Inches		
	Min Circumference 6 Feet From Butt	40.5 Inches		
	Min Diameter At Pole Top	7.321 Inches		
	Min Diameter 6 Feet From Butt	12.8921 Inches		
	Warranty	1 Year		

